





PCT

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY (Chapter II of the Patent Cooperation Treaty)

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference KRC-74PC	FOR FURTHER AC	TION	See Form PCT/IPEA/416	
International application No.	International filing date	(day/month/year)	Priority date (day/month/year)	
PCT/JP2003/010474	19 August 2003	•	20 August 2002 (20.08.2002)	
International Patent Classification (IPC) or national classification and IPC B22D 11/10, 41/52, 41/54, C04B 35/06				
Applicant]	KROSAKIHARIMA	CORPORATIO	N	
This report is the international preli Authority under Article 35 and tran	minary examination repo smitted to the applicant a	rt, established by this according to Article 3	s International Preliminary Examining 6.	
2. This REPORT consists of a total of	4 sheets,	including this cover	sheet.	
3. This report is also accompanied by		_		
a. (sent to the applicant and	l to the International Bur	reau) a total of	sheets, as follows:	
sheets of the des and/or sheets con Administrative Is	ntaining rectifications aut	awings which have the	peen amended and are the basis of this report ority (see Rule 70.16 and Section 607 of the	
sheets which supersede earlier sheets, but which this Authority considers contain an amendment that goes beyond the disclosure in the international application as filed, as indicated in item 4 of Box No. I and the Supplemental Box.				
b. (sent to the International Bureau only) a total of (indicate type and number of electronic carrier(s)) , containing a sequence listing and/or tables related thereto, in computer readable form only, as indicated in the Supplemental Box Relating to Sequence Listing (see Section 802 of the Administrative Instructions).				
4. This report contains indications relating to the following items:				
Box No. I Basis of the report				
Box No. II Priority				
Box No. III Non-establishment of opinion with regard to novelty, inventive step and industrial applicability				
Box No. IV Lack of unity of invention				
Box No. V Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement				
Box No. VI Certain documents cited				
Box No. VII Certain defects in the international application				
Box No. VIII Certain obse	rvations on the internatio	nal application		
Date of submission of the demand		Date of completion	of this report	
19 March 2004 (19.03	3.2004)	01 N	ovember 2004 (01.11.2004)	
Name and mailing address of the IPEA/JP		Authorized officer		
Facsimile No.		Telephone No.		



International application No.

PCT/JP2003/010474

Box No.	Basis of the report	
1. With a othery	regard to the language, this report is based on the international application in the language in wise indicated under this item.	n which it was filed, unless
	This report is based on translations from the original language into the following language which is language of a translation furnished for the purpose of:	age,
	international search (under Rules 12.3 and 23.1(b))	
İ	publication of the international application (under Rule 12.4)	ļ
	international preliminary examination (under Rules 55.2 and/or 55.3)	
furnis	regard to the elements of the international application, this report is based on (replace shed to the receiving Office in response to an invitation under Article 14 are referred to in are not annexed to this report): The international application as originally filed/furnished	ement sheets which have been this report as "originally filed"
	the description:	
1	pages	, as originally filed/furnished
	pages* received by this Authority on pages*	
	the claims:	
•	pages	, as originally filed/furnished
ł	nages*	rith any statement) under Article 19
	pages* received by this Authority on	
l 🖳		
	the drawings:	
	pages* received by this Authority on	, as originally filed/furnished
	pages* received by this Authority on	
▎╙	a sequence listing and/or any related table(s) - see Supplemental Box Relating to Sequence	: Listing.
3.	The amendments have resulted in the cancellation of:	
	the description, pages	
	the claims, Nos.	
1	the drawings, sheets/figs	
	the sequence listing (specify):	
	any table(s) related to sequence listing (specify):	
1		
4.	This report has been established as if (some of) the amendments annexed to this report a made, since they have been considered to go beyond the disclosure as filed, as indica (Rule 70.2(c)). the description, pages the claims, Nos the drawings, sheets/figs	and listed below had not been ted in the Supplemental Box
	the sequence listing (specify):	
	any table(s) related to sequence listing (specify):	
* If ite	em 4 applies, some or all of those sheets may be marked "superseded."	

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

Internati	pplication No.
PCT/JP	03/10474

V.	Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability;
	citations and explanations supporting such statement

Statement			
Novelty (N)	Claims	1, 2	YES
•	Claims		NO
Inventive step (IS)	Claims		YES
	Claims	1, 2	NO NO
Industrial applicability (IA)	Claims	1, 2	YES
	Claims		NO

2. Citations and explanations

The documents cited in the international search report are referred to as "document 1" to "document 4" below.

- Document 1: JP 7-40015 A (Shinagawa Refractories Co., Ltd.), 10 February 1995
- Document 2: JP 61-256961 A (Shin Nihon Kagaku Kogyo Kabushiki Kaisha), 14 November 1986
- Document 3: JP 4-28462 A (Harima Ceramic Co., Ltd.), 31

 January 1992
- Document 4: JP 6-247767 A (Shinagawa Refractories Co., Ltd.), 6 September 1994

Claims 1 and 2

The invention set forth in claims 1 and 2 does not involve an inventive step in the light of documents 1 and 2.

Document 1 (fig. 1 (a) and paragraphs 0011 to 0026) sets forth a method of manufacturing an immersion nozzle for continuous casting, wherein a "ZrO2-C material" is used as the powder line portion, and a refractory comprising mainly calcium zirconate clinker is installed in the inner holes, and said refractory supplies CaO according to the quantity of alumina in the steel.

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

In addition, document 2 (page 2, upper left column, line 14 to upper right column, line 3 and page 3, upper left column, line 12 to page 8, upper left column, line 13) indicates that calcia clinker containing for example 97.20% by weight or 69.60% by weight of CaO is heated in the presence of CO₂, carbonating the surface of CaO to form a CaCO₃ layer with a thickness of 0.05 to 4µm, thereby improving the take-up resistance of the CaO which is removed to a large degree by the Al₂O₃ in molten steel.

That being the case, it would not be particularly difficult for a person skilled in the art to apply the calcia clinker which as formed a CaCO₃ layer described in document 2 as an alternative to the aforementioned refractory set forth in document 1.

Moreover, document 3 (fig. 2 and page 7, upper right column, line 19 to lower left column, line 9 and page 6, upper left column to upper right column) sets forth in the same way as document 1 a method for manufacturing an immersion nozzle for continuous casting, wherein a "ZrO2-C refractory" is used in the "powder line portion (6)", and a "ZrO2-CaO-C refractory (fused substance)" is used in the inner holes, and document 4 (paragraphs 0004 to 0005) indicates that the calcia surface is reacted with carbon dioxide to create a coating of calcium carbonate with a thickness of 1µm or less, and preventing the take-up of CaO.



特 許 協 力 条 約

REC'D	18	ИОИ	2004
-------	----	-----	------


NIPO	PCT

PCT

特許性に関する国際予備報告 (特許協力条約第二章)

(法第12条、法施行規則第56条) [PCT36条及びPCT規則70]

出願人又は代理人 の告類記号 KRC-74PC	今後の手続きについては、様式PCT/IPEA/416を参照すること。
国際出願番号 PCT/JP03/10474	国際出願日 (日.月.年) 19.08.2003 (日.月.年) 20.08.2002
国際特許分類 (IPC) Int.Cl ⁷ B221	1/10, B22D41/52, B22D41/54, C04B35/06
出願人 (氏名又は名称) 黒崎播磨株式	÷社
1. この報告書は、PCT35条に基づき	この国際予備審査機関で作成された国際予備審査報告である。
法施行規則第57条 (РСТЗ6条) σ	見定に従い送付する。
2. この国際予備審査報告は、この表紙を	含めて全部で 3 ページからなる。
3. この報告には次の附属物件も添付され a 附属書類は全部で	Cいる。 ページである。
□ 補正されて、この報告の基礎 囲及び/又は図面の用紙(P	とされた及び/又はこの国際予備審査機関が認めた訂正を含む明細書、請求の範 C T 規則70.16及び実施細則第607号参照)
第 I 欄 4. 及び補充欄に示し 国際予備審査機関が認定した	とように、出願時における国際出願の開示の 範囲を超えた補正を含むものとこの 色替え用紙
b 電子媒体は全部で 配列表に関する補充欄に示すよ ブルを含む。(実施細則第80	うに、コンピュータ読み取り可能な形式による配列表又は配列表に関連するテー 2 号参照)
4. この国際予備審査報告は、次の内容を	- \$፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟፟
□ 第17個 発明の単一性のク	は産業上の利用可能性についての国際予備審査報告の不作成 如 二規定する新規性、進歩性又は産業上の利用可能性についての見解、それを裏付 び説明
国際予備審査の請求書を受理した日	同
19.03.2004	国際予備審査報告を作成した日 01.11.2004
名称及びあて先 日本国特許庁 (IPEA/JP) 郵便番号100-8915 東京都千代田区霞が関三丁目4番	特許庁審査官(権限のある職員) 4E 8727 中 澤 登



国際出願番号 PCT/JP03/10474

第 I 欄 報告の基礎	
1. この国際予備審査報告は、下記に示す場合を除くほ	か、国際出願の意転を共構とした
この報告は、 語による翻訳文 それは、次の目的で提出された翻訳文の言語であ PCT規則12.3及び23.1(b)にいう国際調査	を基礎とした。
□ PCT規則12.4にいう国際公開□ PCT規則55.2又は55.3にいう国際予備審査	_
2. この報告は下記の出願舎類を基礎とした。(法第69 た差替え用紙は、この報告において「出願時」とし、この	条(PCT14条)の規定に基づく命令に応答するために提出され の報告に添付していない。)
× 出願時の国際出願書類	
□ 明細書第 ページ、第 ページ	出願時に提出されたもの
第 ページ*、	付けで国際予備審査機関が受理したもの
間求の範囲	一一一一一 パグス 国际 1 帰 番 遺 機関が 文座 したもの
第	出願時に提出されたもの PCT19条の規定に基づき補正されたもの
第	付けで国際予備審査機関が受理したもの
	付けで国際予備審査機関が受理したもの
第・ページ/図	·
第 ページ/図、	出願時に提出されたもの
第 ページ/図*、	一一一一一 付けで国際予備審査機関が受理したもの
■ 配列表又は関連するテーブル 配列表に関する補充欄を参照すること。 3. ■ 補正により、下記の書類が削除された。	
。	
明細書 第	ページ
□ 請求の範囲 第 □ 図面 第	項 ページ/図
配列表(具体的に記載すること)	
配列表に関連するテーブル(具体的に記載す	すること)
4. この報告は、補充欄に示したように、この報告に えてされたものと認められるので、その補正がさ	こ添付されかつ以下に示した補正が出願時における開示の範囲を超されなかったものとして作成した。 (PCT規則70.2(c))
□ 明細魯 第	ページ
間球の範囲第一	
□ 図面 第□ 配列表 (具体的に記載すること)	ページ/図
□ 配列表に関連するテーブル(具体的に記載す	すること)
* 4. に該当する場合、その用紙に "superseded" と記	入されることがある。



国際出願番号 PCT/JP03/10474

1. 見解			
新規性 (N)	請求の範囲 <u>1</u>	, 2	_ 有 _ 無
進歩性(IS)	請求の範囲 請求の範囲 1	, 2	_ 有 _ 無
産業上の利用可能性(IA)	請求の範囲 1, 請求の範囲	, 2	_ 有

国際調査報告で引用された文献を以下に「文献1」~「文献4」と記す。

文献1:JP 7-40015 A(品川白煉瓦株式会社), 1995. 02. 10

文献 2:JP

61-256961 A(新日本化学工業株式会社),1986.11.14 4-28462 A(ハリマセラミック株式会社),1992.01.31 文献 3: JP 6-247767 A(品川白煉瓦株式会社), 1994.09.06 文献4:JP

請求の範囲1、2

請求の範囲1、2に係る発明は、文献1、2に記載されていることから進歩性を 有しない。

文献1の第1 (a) 図及び0011-0026欄には、連続鋳造用の浸漬ノズル の材質に関して、パウダーライン部に「ZrO2-C材質」を用い、内孔にカルシ ウムジルコネート系グリンカーを主とする耐火物を設置し、該耐火物が鋼中アルミ ナ量に応じてCaOを供給することが示されている。

また、文献2の2頁左上欄第14行一同頁右上欄3行及び第3頁左上欄12行一 第8頁左上欄13行には、CaOを例えば97.20或いは69.60重量%含むカルシア質クリンカーをCO2の存在下で加熱してCaOの表面を炭酸化して厚さ 0.05-4μmのCaCO3層を形成し、溶鋼中のA12O3の除去性の高いCa 〇の耐消化性を向上させ得ることが示されている。

そうであれば、文献1に示される上記耐火物に代えて、文献2に示されるCaC O3層を形成したカルシア質クリンカーを適用することに格別の困難性は見いだせ ない。

なお、文献3の第2図及び第7頁右上欄19行一同頁左下欄第9行及び第6頁左 上欄一同頁右上欄には、連続鋳造用浸漬ノズルの材質に関して、文献1と同様に 「パウダーライン部6」に「ZrO2-C質耐火物」を用い、内孔に「ZrO2-C a O - C質耐火物 (電融物)」を用いることが示されており、文献4の0004-0005欄には、カルシアの表面を二酸化炭素と反応させて厚含1µm以下の炭酸 カルシウムを被覆してCaOの消化を防ぐことが示されている。